

ARL iSpark 8820

Optical Emission Spectrometer

Iron and Steel



The latest Thermo Scientific™ ARL iSpark™ 8820 combines cost effectiveness with high quality, performance and reliability. It is configured to optimally address the needs of companies analyzing **low alloy steel and cast iron** samples.

Designed to meet your needs

With an installed base of over 10,000 units worldwide, the Thermo Scientific ARL OES spectrometers are the reference in terms of performance, stability, reliability and lifetime. The ARL iSpark 8820 is the worthy successor to the ARL 3460 and ARL 4460, by including the famous 1m vacuum PMT optics and most of the attributes that have made their reputation. Thanks to improved spark source, analytical stand, argon management, and various other innovative hardware and software features (see ARL iSpark brochure), it offers performance and stability of its predecessors with reduced cost of ownership and increased functionality.

Your benefits

- True calibration and thorough performance testing in our factory as your best guarantee of accuracy and performance
- Optimal control of costly alloying and matrix elements and critical trace elements, thanks to outstanding analysis of all the elements at all concentrations
- Unequaled stability for highest confidence in the results with minimal recalibration operations
- Minimal maintenance in complete safety thanks to dedicated maintenance management software
- High instrument availability thanks to low frequency of maintenance and recalibration
- Low cost of ownership, thanks to significant argon savings and low usage of SUS samples
- Fast learning curve of operators and managers
- Exceptional lifetime with continuous upgrade possibilities
- Short payback thanks to superior productivity and savings

The ARL iSpark 8820 provides an immediate cost-effective and high performance “turnkey” solution, ready to analyze on the installation day.



Iron and steel calibrations available with the ARL iSpark 8820 (Fe11)

Elements	Low Alloy Steel	Free Cutting Steel	Cast Iron	Low Alloy Steel for small samples	Elements
Fe	89.6 - 99.9	91.5 - 99.9	79.4 - 95.1	89.6 - 99.9	Fe
Al	0.0006 - 1.9	0.001 - 0.12	0.003 - 0.16	0.0006 - 1.9	Al
As	0.001 - 0.15	0.015 - 0.08	0.002 - 0.16	0.002 - 0.15	As
B	0.0003 - 0.012	0.0015 - 0.012	0.0005 - 0.1	0.0005 - 0.012	B
Bi	0.002 - 0.1	-	0.003 - 0.025	0.002 - 0.1	Bi
C	0.0025 - 1.5	0.03 - 1.3	1.4 - 4.5	0.0025 - 1.5	C
Ca	0.00015 - 0.014	0.0002 - 0.014	-	0.001 - 0.014	Ca
Co	0.0005 - 0.7	0.005 - 0.23	0.004 - 0.45	0.002 - 0.7	Co
Cr	0.0015 - 2.5	0.006 - 2.5	0.02 - 2.2	0.0015 - 2.5	Cr
Cu	0.002 - 1.5	0.006 - 0.7	0.01 - 2.7	0.002 - 1.5	Cu
Mn	0.001 - 2.4	0.05 - 1.9	0.06 - 1.9	0.001 - 2.4	Mn
Mo	0.001 - 1.6	0.002 - 1	0.003 - 2	0.004 - 1.6	Mo
Nb	0.001 - 0.8	0.006 - 0.07	0.003 - 0.55	0.001 - 0.8	Nb
Ni	0.001 - 2.2	0.007 - 2.2	0.02 - 2.5	0.005 - 2.2	Ni
P	0.001 - 0.12	0.009 - 0.08	0.003 - 1.2	0.002 - 0.12	P
Pb	0.0008 - 0.2	0.0015 - 0.35	0.0015 - 0.06	0.002 - 0.2	Pb
S	0.0005 - 0.14	0.009 - 0.35	0.0015 - 0.22	0.002 - 0.14	S
Sb	0.0015 - 0.25	-	0.0015 - 0.29	0.002 - 0.25	Sb
Si	0.0015 - 3.3	0.002 - 1.8	0.25 - 4	0.0015 - 3.3	Si
Sn	0.0008 - 0.25	0.001 - 0.13	0.002 - 0.4	0.002 - 0.25	Sn
Ti	0.0005 - 0.6	0.002 - 0.12	0.0015 - 0.3	0.001 - 0.6	Ti
V	0.002 - 1.1	0.002 - 0.6	0.002 - 0.7	0.005 - 1.1	V
W	0.005 - 1.7	0.05 - 0.35	0.005 - 0.2	0.005 - 1.7	W
Zn	0.001 - 0.04	-	0.001 - 0.03	0.003 - 0.04	Zn
Zr	0.001 - 0.25	0.006 - 0.08	0.001 - 0.05	0.003 - 0.25	Zr

Notes:

- Determination of Al, B, Ca and Ti soluble/insoluble in low alloy steel in option
- Inclusion analysis methods in option
- Thermo Fisher Scientific reserves the right to modify the calibration ranges according to the availability of certified reference materials.

Find out more at thermofisher.com/ispark

©2018 Thermo Fisher Scientific Inc. All rights reserved. All trademarks are the property of Thermo Fisher Scientific. This information is presented as an example of the capabilities of Thermo Fisher Scientific products. It is not intended to encourage use of these products in any manner that might infringe the intellectual property rights of others. Specifications, terms and pricing are subject to change. Not all products are available in all countries. Please consult your local sales representative for details.

PS41361-EN 1118

ThermoFisher
SCIENTIFIC